



# 重量表

## 鋼板重量表 (kg/枚)

厚さ(mm)	単位重量 (kg/㎡)	914×1829 (3×6)	1219×2438 (4×8)	1524×3048 (5×10)
0.3	2.355	3.94	7.00	10.9
0.4	3.140	5.25	9.33	14.6
0.5	3.925	6.56	11.7	18.2
0.6	4.710	7.88	14.0	21.9
0.7	5.495	9.19	16.3	25.5
0.8	6.280	10.5	18.7	29.2
0.9	7.065	11.8	21.0	32.8
1.0	7.850	13.1	23.3	36.5
1.2	9.420	15.8	28.0	43.8
1.6	12.56	21.0	37.3	58.3
2.0	15.70	26.3	46.7	72.9
2.3	18.06	30.2	53.7	83.9
3.2	25.12	42.0	74.7	117
4.0	31.40	52.5	93.3	146
4.5	35.32	59.1	105	164
5.0	39.25	65.6	117	182
6.0	47.10	78.8	140	219
7.0	54.95	91.9	163	255
8.0	62.80	105	187	292
9.0	70.65	118	210	328
10.0	78.50	131	233	365
11.0	86.35	144	257	401
12.0	94.20	158	280	438
13.0	102.0	171	303	474
14.0	109.9	184	327	510
15.0	117.8	197	350	547
16.0	125.6	210	373	583

比重=7.85

## ステンレス鋼板重量表 (kg/枚)

厚さ(mm)	1000×2000 (1m×2m)		1219×2438 (4×8)		1524×3048 (5×10)
	SUS304	SUS316	SUS304	SUS316	SUS304
0.3	4.76	4.79	7.07	7.11	11.1
0.4	6.34	6.38	9.43	9.49	14.7
0.5	7.93	7.98	11.8	11.9	18.4
0.6	9.52	9.58	14.1	14.2	22.1
0.7	11.1	11.2	16.5	16.6	25.8
0.8	12.7	12.8	18.9	19.0	29.5
0.9	14.3	14.4	21.2	21.3	33.2
1.0	15.9	16.0	23.6	23.7	36.8
1.2	19.0	19.2	28.3	28.5	44.2
1.5	23.8	23.9	35.4	35.6	55.3
2.0	31.7	31.9	47.1	47.4	73.7
2.5	39.7	39.9	58.9	59.3	92.1
3.0	47.6	47.9	70.7	71.1	111
4.0	63.4	63.8	94.3	94.9	147
5.0	79.3	79.8	118	119	184
6.0	95.2	95.8	141	142	221
7.0	111	112	165	166	258
8.0	127	128	189	190	295
9.0	143	144	212	213	332
10.0	159	160	236	237	368
12.0	190	192	283	285	442

比重：SUS304=7.93、SUS316=7.98

## 亜鉛メッキ鋼板重量表 (kg/枚)

記号	Z27		
	厚さ(mm)	914×1829 (3×6)	1219×2438 (4×8)
0.27	4.18	7.43	11.6
0.3	4.57	8.13	12.7
0.35	5.23	9.30	14.5
0.4	5.89	10.5	16.4
0.5	7.20	12.8	20.0
0.6	8.51	15.1	23.6
0.8	11.1	19.8	30.9
1.0	13.8	24.5	38.2
1.2	16.4	29.1	45.5
1.6	21.6	38.5	60.1
2.0	26.9	47.8	74.7
2.3	30.8	54.8	85.6
3.2	42.6	75.8	118
4.0	53.1	94.5	148
4.5	59.7	106	166

亜鉛付着量 Z27=381g/㎡

## アルミ板重量表 (kg/枚)

記号	A1050P			A5052P		
	厚さ(mm)	1000×2000 (1m×2m)	1220×2440 (4×8)	1525×3050 (5×10)	1000×2000 (1m×2m)	1250×2500 (4×8)
0.3	1.63					
0.4	2.18					
0.5	2.72	4.05	6.33	2.69		
0.6	3.26	4.86	7.59			
0.8	4.35	6.48	10.1	4.30	6.73	
1.0	5.44	8.10	12.7	5.38	8.41	
1.2	6.53	9.72	15.2	6.46	10.1	
1.5	8.16	12.1	19.0	8.07	12.6	
2.0	10.9	16.2	25.3	10.8	16.8	
2.5	13.6	20.2	31.6	13.5		
3.0	16.3	24.3	38.0	16.1	25.2	
4.0	21.8	32.4	50.6	21.5	33.6	
5.0	27.2	40.5	63.3	26.9	42.0	
6.0	32.6	48.6	75.9	32.3	50.4	
8.0	43.5	64.8	101	43.0	67.3	
10.0	54.4	81.0	127	53.8	84.1	
12.0	65.3	97.2	152	64.6	101	
15.0	81.6	121	190	80.7	126	
20.0	109	162	253	108	168	

比重：A1050=2.72、A5052=2.69

## 黄銅板重量表 (kg/枚)

厚さ(mm)	365×1200	1000×2000
0.5	1.86	8.50
0.6	2.23	10.2
0.7	2.61	11.9
0.8	2.98	13.6
1.0	3.72	17.0
1.2	4.47	20.4
1.5	5.58	25.5
2.0	7.45	34.0
2.5	9.31	42.5
3.0	11.2	51.0
3.5	13.0	59.5
4.0	14.9	68.0
5.0	18.6	85.0
6.0	22.3	102.0

黄銅比重：C280(BSP) 8.43

## 銅板重量表 (kg/枚)

厚さ(mm)	365×1200	1000×2000
0.5	1.95	8.9
0.6	2.34	10.7
0.7	2.73	12.5
0.8	3.12	14.2
0.9	3.508	16.02
1.0	3.90	17.8
1.2	4.68	21.4
1.5	5.85	26.7
2.0	7.89	35.6
2.5	9.75	44.5
3.0	11.7	53.4
3.5	13.6	62.3
4.0	15.6	71.2
5.0	19.5	89.0
6.0	23.4	107

銅比重：C1100P(CUP) 8.89